



Technical data sheet

Article No.: **12544**
 Leaflet No.: 1953
 Version: 09


POLYFLEX® PES-135 Pearl-Metallic smooth texture Corona Silk-gloss

Pearl metallic powder coatings for exterior use on polyester base with excellent light and weather resistance, very good flow and excellent opacity. Stabilized against discoloration and burning gas-fired curing ovens in directly. Curing can be done already from 180 ° C.

Applications	Metal facade, aluminium profile, sun protection system, windows, doors, gates and frames any many more.
Colours	According to special Pearl Metallic color cards. Special colors on request.
Surface	smooth texture
Gloss	Silk-gloss
Powder properties	<p>Particle size distribution smaller 29 µm: 40 – 47 % <small>(HELOS H1708)</small> smaller 122 µm: 96 – 100%</p> <p>Density 1.4 – 1.8 g/cm³ can vary depending on the colour; can be specified for each individual colour</p>
Material consumption	g/m ² = Density (g/cm ³) x Film thickness (µm)
Coating thickness	<p>Recommended 60 – 80 µm depending on the colour</p> <p>Maximum 120 µm</p>
Application	<p>The application can be made with the usual electrostatic powder coating systems. The Tribo processing is not recommended due to effect shifts.</p> <p>Please observe our application instructions for POLYFLEX powder paint with metallic effect VR003D.</p> <p>To avoid any surface disturbances we recommend not to mix this type of powder paint with any other powder.</p>
Packaging	<ul style="list-style-type: none"> - 20/25 kg cardboard - 500 kg Octobox - 450/500 kg Big Bag <p>Other packaging variations are available on request.</p>

Baking diagram

Curing time recommendation: 15 min by 180 °C object temperature



Curing conditions:
 200°C 10 min. hold time
 190°C 12 min. hold time
 180°C 15 min. hold time

Supports

Different metals, however mainly on pre-treated aluminum or hot-dip galvanized or powder coated or anti-corrosion dip-coated steel. The support to be coated has to be free of oil, grease and oxidation products. Under exposure to corrosion, we recommend the following pre-treatment:

Aluminum Chromating, chrom free pre-treatment or thin layer of anodizing coat

Steel/Iron Galvanization with subsequent chromating

Physical properties

tested on:

Aluminium plate 0,8 mm AlMg1
H14 chromated

Film thickness
60 – 80 µm

Cross cut test GT 0
(DIN ISO 2409)

Mandrel bending test < 5 mm
(DIN ISO 1519)

Impact resistance front > 5,0 Nm (~44 inchpound)
ASTM D 2794 reverse > 2,5 Nm (~22 inchpound)

Erichsen cupping > 5 mm
(DIN ISO 1520)

Buchholz hardness > 90
(DIN ISO 2815)

Resistance

tested on:

Aluminium plate 0,8 mm AlMg1
H14 chromated

Condensation water test 1000 h no bubble building
DIN ISO 6270 Infiltration on the scratch track under 1 mm

Salt spray test 1000 h no bubble building
DIN ISO 9227 Infiltration on the scratch track under 1 mm

Material approvals

GSB Standard 115h

Qualicoat Class 1 P-0153

Post treatment of coated parts

To print, to paste, to label, to laminate with film, over-coating and other post-treatments, some preliminary testing is recommended. For packaging only use appropriate plasticizers free materials. Condensation must be avoided.

Repairs

For repairs (conveyors hangers touch ups) the repair kit, art. No 12155 is available.

Storage

Storage instruction: In the original containers, store in a cool and dry environment by max. 25 °C. No direct sun exposure.

Shelf life 18 months from the date of production under the mentioned conditions

Safety recommendations

Under explosion limit 40 g/m³

Further information are to find in the safety data sheet and the CEPE booklet „Safe powder coating“ and „Results of experimental toxicology study on thermosetting powder coatings“.

Comments:

The information on this technical data sheet relative to the properties and application of the product concerned are made on hand of our knowledge, development and practical experience. Because of the multiple possible applications, it is impossible for us to present them all in detail. Our technical consultants are at your disposal for any question you might have. Furthermore, our general sales and delivery conditions apply.

This technical data sheet is revised periodically. If necessary, our sales department will confirm the validity of this document.



KARL BUBENHOFER AG, Hirschenstrasse 26, CH-9201 Gossau SG
Tel. +41 (0)71 387 41 41, Fax +41 (0)71 387 43 05, www.kabe-farben.ch